



"WORLD-CLASS ANODES"

WINCA-G-E

Graphite Anodes

Chemical Composition (%)

Element	Carbon	Ash
Content (%)	99.8	0.2

Physical Properties

Max Grain Size (in.)	Bulk Density (g/cm ³)	Resistivity (ohm. in.)	Flexural Strength (PSI)	Porosity (%)
0.06	1.6 - 1.7	3.0×10^4	2,300	18

ROD	Dimensions		Weight (lb)
	A (in.)	B (in.)	
	3	30	13
	3	60	27
	4	40	31
	4	80	62